

# Tgard™ 300 Series Thermally Conductive Insulators



#### HIGH PERFORMANCE THERMAL INTERFACE PRODUCTS

Tgard<sup>™</sup> 300 is a medium thermal performance insulator pad consisting of a ceramic high temperature silcone rubber coated on electrical fiberglass.

Tgard 300 is specifically designed for applications that require low component mounting forces. The unique formulation will enhance thermal performance which minimizes thermal resistance at low mounting forces. The unique coating formulation offers an excellent mating surface for low pressure clip mounting applications.

## **FEATURES AND BENEFITS**

- High breakdown voltage of 6,000 volts AC
- Thermal resistance of 0.50° C-in2/watt at 50 psi
- Unique coating formulation offers low mounting forces
- Unifying benefits of thermal & electrical performance for general-purpose applications

### **APPLICATIONS**

- Switching mode power supplies
- Industrial equipment
- Motor controls

Americas: +1.847 839.6907 IAS-AmericasEastSales@lairdtech.com

Europe: +44.1628.858941
IAS-EUSales@lairdtech.com
Asia: ++86.21.5855.0827.127
IAS-AsiaSales@lairdtech.com
CLV-customerservice@lairdtech.com
www.lairdtech.com/thermal



# **Tgard™ 300 Series Thermally Conductive Insulators**

PROPERTIES	TEST M	TEST METHOD		METRIC VALUES		IMPERIAL VALUES	
ELECTRICAL PROPERTIES							
Dielectric withstand voltage 50mm probe for 30 sec	ASTM D149		4,500 volts DC		C	4,500 volts DC	
Dielectric breakdown voltage 50mm probe	ASTM D149		Avg >6,000 volts AC			Avg >6,000 volts AC	
Volume resistivity	ASTN D257		10 <sup>12</sup> ohm-cm		n	10 <sup>12</sup> ohm-in	
Dielectric constant @1Mhz	ASTN	ASTN D257		3.3		3.3	
Electrical RTI temperature rating	UL746D		150ºC			302ºF	
MECHANICAL PROPERTIES							
Thickness			0.23 mm			0.009 in	
Hardness	ASTM D2240		75 Shore A			75 Shore A	
Tensile strength	ASTM D412		10 Mpa			1.5 Kpsi	
Elongation @ 45º to warp/fill	ASTM D412		20%			20%	
Elongation along width or length	ASTM D412		5%			5%	
Operating temperature range		-60º to 180ºC		С	-76º to 356ºF		
Color			Yellow			Yellow	
UL flammability rating	UL	UL 94		V-0		V-0	
PRESSURE	UNITS	10 (69)	25 (172)	50 (345)	100 (689)	200 (1379)	400 (2758)
TOTAL THERMAL RESISTANCE							
Modified ASTM D5470	ºC-in²/watt	0.62	0.57	0.50	0.41	0.34	0.30
Modified ASTM D5470	C-cm²/watt	4.00	3.68	3.09	2.65	2.19	1.94
T0-220	ºC/watt	1.17	0.92	0.83	0.81	0.80	0.76

Standard thickness:

9 mils (0.229 mm)

Configurations available:

- Sheet form, roll form and die-cut parts
- Single-side, pressure-sensitive adhesive on request

Standard options:

- Without adhesive (A0): 12 x 18" sheets, 12" x 65M, 12" x 30M roll or custom configuration
- With adhesive (A1): 11.75 x 18" sheets, 11.75" x 30M roll or custom configuration